

TAMURA  
Appl. No. 09/766,318  
February 9, 2004

**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A heat-resistant glass fiber which has a composition ~~comprising~~consisting essentially of, by weight %, 56 to 58.5% of  $\text{SiO}_2$ , 12 to 17% of  $\text{Al}_2\text{O}_3$ , 16 to 27% of  $\text{CaO}$ , 1 to 9% of  $\text{MgO}$ , 0 to 1% of  $\text{Na}_2\text{O}$  and 0 to 1% of  $\text{K}_2\text{O}$  as the entirety of the fiber and containing neither  $\text{B}_2\text{O}_3$  nor  $\text{F}_2$ , and which has a surface layer portion made of a silicic glass having an  $\text{SiO}_2$  content of at least 90% by weight, wherein the fiber substantially retains its flexibility when heated for ten hours at 900°C.

2. (Original) The heat-resistant glass fiber of claim 1, wherein the surface layer portion made of a silicic glass having an  $\text{SiO}_2$  content of at least 90% by weight has a thickness of 0.1 to 1.0  $\mu\text{m}$ .

3. (Original) The heat-resistant glass fiber of claim 1, wherein a difference  $\Delta T$  between a spinning temperature which is a melting temperature of a glass having a viscosity of 100 Pa·s and a liquidus temperature is at least 30°C.

4. (Original) A process for the production of the heat-resistant glass fiber recited in claim 1, which comprises treating the surface of a glass fiber which has a composition comprising, by weight %, 56 to 58.5% of  $\text{SiO}_2$ , 12 to 17% of  $\text{Al}_2\text{O}_3$ , 16 to 27% of  $\text{CaO}$ , 1 to 9% of  $\text{MgO}$ , 0 to 1% of  $\text{Na}_2\text{O}$  and 0 to 1% of  $\text{K}_2\text{O}$  and containing neither  $\text{B}_2\text{O}_3$  nor  $\text{F}_2$ , with a mineral acid.

TAMURA

Appl. No. 09/766,318

February 9, 2004

5. (Original) The process of claim 4, wherein the treatment is carried out by immersing the glass fiber in an aqueous solution containing, as the mineral acid, 1 to 10% by weight of at least one acid selected from HCl, H<sub>2</sub>SO<sub>4</sub> or HNO<sub>3</sub> at a temperature of 0 to 90°C.

6. (Currently Amended) A heat-resistant glass fiber which has a surface layer portion at least 0.01 µm thick, made of silicic glass having an SiO<sub>2</sub> content of at least 90%, the balance of the glass fiber having a composition ~~comprising~~ consisting essentially of, by weight %, 56 to 58.5% of SiO<sub>2</sub>, 12 to 17% of Al<sub>2</sub>O<sub>3</sub>, 16 to 27% of CaO, 1 to 9% of MgO, 0 to 1% of Na<sub>2</sub>O and 0 to 1% of K<sub>2</sub>O as the entirety of the fiber and containing neither B<sub>2</sub>O<sub>3</sub> nor F<sub>2</sub> wherein the fiber substantially retains its flexibility when heated for ten hours at 900°C.